



Florida
Test



Total duration:
12 months



EXPOSURE PERIOD:

FROM: **03/04/2013**

TO: **01/04/2014**

LAB. ID NUMBER: 29201
POWDER COATING: Saltlake-016
HEAT TRANSFER FILM: --
Colour variation (ΔE): **1,18**
residual gloss: **100%**

Technical Remarks

Excellent residual gloss and low colour variation (ΔE)
(\pm RAL 5022/4007)

Technical Opinion:

Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

QUALICOAT REQUIREMENTS

The residual gloss shall be at least 50% of the original gloss.
The ΔE values shall not exceed the maximum values prescribed in the annexed table (see Appendix A7 of Qualicoat Specifications).

Unexposed area
(reference)

Exposed
area

