Florida Test

Total duration: 12 months

EXPOSURE PERIOD:

FROM: **03/04/2013**

TO: **01/04/2014**

LAB. ID NUMBER: 29539
POWDER COATING: Wallsky-009
HEAT TRANSFER FILM: --
Colour variation (ΔE): **2,76**
residual gloss: **54%**

Technical Remarks

Sufficient residual gloss and low colour variation (ΔE) (±RAL 9005)

Technical Opinion:

Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

QUALICOAT REQUIREMENTS
The residual gloss shall be at least 50% of the original gloss. The ΔE values shall not exceed the maximum values prescribed in the annexed table (see Appendix A7 of Qualicoat Specifications).