Florida Test

Total duration: 12 months

EXPOSURE PERIOD:

FROM: **27/11/2015**

TO: **19/12/2016**

LAB. ID NUMBER: 38271
POWDER COATING: Glass-008
HEAT TRANSFER FILM: --
Colour variation (ΔE): **4,24**
residual gloss: **98%**

Technical Remarks

Excellent residual gloss and low colour variation (ΔE).

Technical Opinion:

Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

QUALICOAT REQUIREMENTS
The residual gloss shall be at least 50% of the original gloss. The ΔE values shall not exceed the maximum values prescribed in the annexed table (see Appendix A7 of Qualicoat Specifications).