Test Report: Accelerated Weathering Test

GiColor S.r.l.

240

Laboratory Test

No. 386

Device: QSun 3000

Total duration: 1046h



LAB. ID NUMBER: 32178
POWDER COATING: Picasso-003
HEAT TRANSFER FILM: --
Grey scale: **5/4**
residual gloss: **100%**

Technical Remarks

Excellent residual gloss and very low colour variation , after 1046 hours on sample.

Technical Opinion:

Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.