



Florida
Test



Total duration:
12 months



EXPOSURE PERIOD:

FROM: **24/09/2014**

TO: **01/10/2015**

LAB. ID NUMBER: 35253
POWDER COATING: 6.666.3345-GJT
HEAT TRANSFER FILM: --
Colour variation (ΔE): **1,21**
residual gloss: **52%**

Technical Remarks

Sufficient residual gloss and low colour variation (ΔE)

Technical Opinion:

Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

QUALICOAT REQUIREMENTS

The residual gloss shall be at least 50% of the original gloss.

The ΔE values shall not exceed the maximum values prescribed in the annexed table (see Appendix A7 of Qualicoat Specifications).

Unexposed area
(reference)

Exposed
area

