



Laboratory  
Test


No. 620



Device:  
QSun3000



Total duration:  
1206 h



LAB. ID NUMBER: 51794  
POWDER COATING: Veranda-104  
HEAT TRANSFER FILM: --  
Colour Variation ( $\Delta E$ ): **0,69**  
residual gloss: **100%**

### Technical Remarks

Excellent residual gloss and low colour variation ( $\Delta E$ ), after 1206 hours on sample.

Technical Opinion:

**Suitable for  
OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.