



Laboratory  
Test


No. 480



Device:  
Sol 3000e



Total duration:  
1188h



LAB. ID NUMBER: 41191  
POWDER COATING: Materico-009  
HEAT TRANSFER FILM: --  
Colour Variation ( $\Delta E$ ): **0,03**  
residual gloss: **96%**

#### Technical Remarks

Excellent residual gloss and low colour variation ( $\Delta E$ ), after 1188 hours on sample.

Technical Opinion:

**Suitable for  
OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.