



Laboratory
Test


No. 465



Device:
Sol 3000eN



Total duration:
1108h



LAB. ID NUMBER: 39986
POWDER COATING: 6.447.0612-AJT + 6.447.0015-AJT
HEAT TRANSFER FILM: --
Colour Variation (ΔE): **0,38**
residual gloss: **72%**

Technical Remarks

Good residual gloss and very low colour variation (ΔE), after 1108 hours on sample.

Technical Opinion:

**Suitable for
OUTDOOR USE**

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers. However, the resistance against accelerated weathering test is only one of the conditions necessary for the evaluation of the resistance of the finished product. For a final assessment see further analysis on natural exposure in Florida.