



**Florida
Test**



**Total duration:
12 months**



EXPOSURE PERIOD:

FROM: 21/03/2018

TO: 22/03/2019

LAB. ID NUMBER: 42871
POWDER COATING: Materico-112
HEAT TRANSFER FILM: --
Colour variation (ΔE): **1,49**
residual gloss: 90%

Technical Remarks

Excellent residual gloss and low colour variation (ΔE)

Technical Opinion:

Suitable for OUTDOOR USE

Test was carried on samples prepared according to technical specifications supplied by raw materials manufacturers.

QUALICOAT REQUIREMENTS

The residual gloss shall be at least 50% of the original gloss.
The ΔE values shall not exceed the maximum values prescribed in the annexed table (see Appendix A7 of Qualicoat Specifications).

